

Appl. No. : 09/228,325
Filed : January 11, 1999

I. AMENDMENTS TO THE CLAIMS

The following listing of the claims replaces all prior versions and listing of the claims in the application:

1. (Previously presented) A basketball backboard assembly sized and configured for playing the game of basketball comprising:

a backboard frame structure having a bonding surface;

an acrylic backboard having a bonding surface; and

a catalyzed elastomeric adhesive sandwiched between the frame bonding surface and the backboard bonding surface, wherein the elastomeric adhesive provides sufficient adhesion and flexibility to the acrylic backboard and frame structure bonding surface to be used in the game of basketball.

2. (Original) A basketball backboard assembly according to claim 1, wherein the elastomeric adhesive has a bond gap in the range from about 2 to 2.5 mm (0.08 to 0.1 inch).

3. (Cancelled)

4. (Previously presented) A basketball backboard assembly according to claim 1, wherein the elastomeric adhesive is catalyzed adhesive.

Appl. No. : 09/228,325
Filed : January 11, 1999

5. (Previously presented) A basketball backboard assembly according to claim 1, wherein the elastomeric adhesive is a two-part catalyzed adhesive in which the two parts are combined in a ratio to provide a set time in the range from about 7 to 15 minutes.

6. (Previously presented) A basketball backboard assembly according to claim 1, wherein the elastomeric adhesive is a two-part catalyzed adhesive in which the two parts are combined in a ratio to provide a set time in the range from about 5 minutes to 1 hour.

7. (Previously presented) A basketball backboard assembly according to claim 1, further comprising one or more bond gap spacers located between the frame bonding surface and the backboard bonding surface to provide a defined bond gap.

8. (Previously presented) A basketball backboard assembly according to claim 7, wherein the one or more bond gap spacers comprise spherical beads.

9. (Original) A basketball backboard assembly according to claim 8, wherein the spherical beads comprise glass microspheres.

10. (Original) A basketball backboard assembly according to claim 9, wherein the glass microspheres have a diameter in the range from about 2 to 2.5 mm (0.08 to 0.1 inch).

Appl. No. : 09/228,325
Filed : January 11, 1999

11. (Original) A basketball backboard assembly according to claim 1, wherein the backboard frame structure is metal.

12. (Original) A basketball backboard assembly according to claim 1, wherein the backboard frame structure is painted metal.

13. (Original) A basketball backboard assembly according to claim 1, wherein the backboard bonding surface contains a printed image.

14. (Currently Amended) A basketball backboard assembly sized and configured for playing the game of basketball comprising:

a metal backboard frame structure having a bonding surface;

an acrylic backboard having a bonding surface; and

a catalyzed silicone adhesive sandwiched between the frame bonding surface and the backboard bonding surface, wherein the silicone adhesive is configured to provide a set time in the range from about 5 minutes to 1 hour, wherein the silicone adhesive provides sufficient adhesion and flexibility to the acrylic backboard and frame structure bonding surfaces to be used in the game of basketball; and

one or more bond gap spacers located between the frame bonding surface and the backboard bonding surface to provide the bond gap.

Appl. No. : 09/228,325
Filed : January 11, 1999

15. (Original) A basketball backboard assembly according to claim 14, wherein the silicone adhesive is configured to provide a set time in the range from about 7 to 15 minutes.

16. (Previously presented) A basketball backboard assembly according to claim 14, wherein the one or more bond gap spacers comprise spherical beads.

17. (Original) A basketball backboard assembly according to claim 16, wherein the spherical beads comprise glass microspheres.

18. (Original) A basketball backboard assembly according to claim 17, wherein the glass microspheres have a diameter in the range from about 2 to 2.5 mm (0.08 to 0.1 inch).

Claims 19-43 (Cancelled).
